

Coherence Window in the dynamics of Quantum Nanomagnets

P. C. E. Stamp¹, I. S. Tupitsyn²

¹ *Canadian Institute for Advanced Research,
and Physics Dept., University of British Columbia,
6224 Agricultural Rd., Vancouver,
B.C., Canada V6T 1Z1*

² *Russian Science Centre "Kurchatov Institute",
Moscow 123182, Russia*

Decoherence in many solid-state systems is anomalously high, frustrating efforts to make solid-state qubits. We show that in nanomagnetic insulators in large transverse fields, there can be a fairly narrow field region in which both phonon and nuclear spin-mediated decoherence are drastically reduced. As examples we calculate decoherence rates for the *Fe-8* nanomolecule, for *Ni* particles, and for *Ho* ions in *LiHo_xY_{1-x}F₄*. The reduction in the decoherence, compared to low field rates, can exceed 6 orders of magnitude. The results also give limitations on the observability of macroscopic coherence effects in magnetic systems.

PACS numbers:

Decoherence has emerged as a major challenge, both for fundamental physics, and for attempts to make solid-state qubits [1]. Experimental decoherence rates are often much larger than theoretical estimates [2, 3]- in complex systems like conductors or superconductors, many low-energy excitations apart from the usual "oscillator bath" modes [4, 5] can cause phase decoherence. These include charged defects, dislocations, paramagnetic and nuclear spins, external flux and voltage noise, and junction resistance fluctuations. The advantages of solid-state systems (stable circuits, scalability, etc.) cannot be exploited until decoherence effects are suppressed.

It is often assumed that this is purely an engineering problem. However this is not true- even completely pure systems have intrinsic decoherence, and then theory is essential, to see how this can be quantified and controlled. Here we consider a very interesting possibility, involving nanomagnetic insulators. These are often chemically reproducible, so impurities and defects are kept to a minimum- and electronic decoherence is completely absent. We show they also have another crucial feature, viz., the decoherence can be tuned down to very low values. These results are of wide interest, in the search for magnetic materials showing spin coherence phenomena.

1. Intrinsic Decoherence in a nanomagnetic "qubit": At low T the spin Hamiltonian of many large-spin nanomagnetic systems (magnetic molecules, rare earth ions, or nanomagnetic particles) reduces to a 2-state form $\mathcal{H}_o(\hat{\tau}) = (\Delta_o \hat{\tau}_x + \epsilon_o \hat{\tau}_z)$, with the Pauli spin $\hat{\tau}$ acting on the 2 lowest spin levels [6, 7]. The spin gap E_G to the next levels is typically $\sim 5 - 10$ K, and the 2-state picture is valid at energies $\ll E_G$. At higher energies the individual electronic spins $\{\mathbf{s}_j\}$ are assumed to be locked into a nanospin $\mathbf{S}$ (so that $\mathbf{S} = \sum_j \mathbf{s}_j$) by strong exchange or superexchange interactions. We assume henceforth an "easy $\hat{z}$ -axis" nanomagnet; then the 'bias' energy $\epsilon_o = g\mu_B S_z H_o^z$. When $\epsilon_o = 0$, the splitting

Δ_o between the 2 "qubit" states $|-\rangle, |+\rangle$ (bonding and anti-bonding eigenstates of $\mathcal{H}_o(\hat{\tau})$) is produced by tunneling between 2 potential wells, each well having a "small oscillation" energy Ω_o ; typically $\Omega_o \sim E_G$. We define the states $|\uparrow\rangle, |\downarrow\rangle$ (eigenstates of $\hat{\tau}_z$) by $|\pm\rangle = [|\uparrow\rangle \pm |\downarrow\rangle]/\sqrt{2}$. If the total nanomagnetic spin $\mathbf{S}$ is not too small, these states correspond roughly to semiclassical spin coherent states [8], having orientations $\mathbf{n}_\sigma$ (here $\sigma = \uparrow, \downarrow$), which depend on both the internal anisotropy field of the nanomagnet, and any transverse external field $\mathbf{H}_o^\perp$. The splitting Δ_o depends sensitively on $\mathbf{H}_o^\perp$.

The intrinsic decoherence in insulating nanomagnets comes from entanglement of the nanomagnetic spin wave function with that of the nuclear spins and phonons [10]. Both of these couplings are well understood. The nuclear spins $\{\mathbf{I}_k\}$ couple to the electronic spins $\{\mathbf{s}_j\}$ in $\mathbf{S}$ via individual hyperfine couplings $A_{\alpha\beta}^{jk} s_j^\alpha I_k^\beta$, and the phonons couple to $\mathbf{S}$ via magnetoacoustic (spin-phonon) interactions [9]. Without yet specifying the precise form of the hyperfine couplings (which of course depend on the system being studied) we can define quite generally a vector $\vec{\omega}_k^\parallel$ which specifies the net effect on the k -th nuclear spin $\mathbf{I}_k$, of all the hyperfine fields coming from the individual electronic spins in $\mathbf{S}$:

$$\vec{\omega}_k^\parallel \equiv \omega_k^\parallel \hat{l}_k^\alpha = \frac{1}{2} \sum_j A_{\alpha\beta}^{jk} (\langle s_j^\alpha \rangle^\uparrow - \langle s_j^\alpha \rangle^\downarrow) \quad (1)$$

Here $\hat{l}_k$ is a unit vector in the direction of this total field, with components $\hat{l}_k^\alpha$, and $\langle s_j^\alpha \rangle^\sigma$ is the expectation value of $\mathbf{s}_j$ when $\mathbf{S} \rightarrow \mathbf{S}^\sigma$. We see that when $\mathbf{S}$ flips from $\mathbf{S}^\uparrow$ to $\mathbf{S}^\downarrow$, the energy change is just $2\omega_k^\parallel \hat{l}_k \cdot \mathbf{I}_k$, ie., we have a diagonal coupling $\hat{\tau}_z \omega_k^\parallel \hat{l}_k \cdot \hat{\mathbf{I}}_k$ between the qubit and $\mathbf{I}_k$. One can also write this coupling as $\hat{\tau}_z \xi_z$, where $\xi_z = \omega_k^\parallel \hat{l}_k \cdot \hat{\mathbf{I}}_k$ acts as an extra bias field, in addition to the external bias field ϵ_o . Note that the weak interaction between nuclear spins (typically dipolar) causes slow spin

diffusion between them. The net effect of this is to make $\xi_z \rightarrow \xi_z(t)$, ie., the nuclear bias field acting on the qubit fluctuates in time even when the qubit is frozen. We shall argue below that we can neglect this fluctuation in strong transverse fields.

The $\mathbf{I}_k$ also couple to the external field $\mathbf{H}_o$, with Zeeman coupling $\omega_k^\perp \hat{m}_k \cdot \hat{\mathbf{I}}_k$, where

$$\omega_k^\perp \hat{m}_k = g_k^N \mu_N \mathbf{H}_o \quad (2)$$

and $\hat{m}_k$ is a unit vector along $\mathbf{H}_o$.

If we now take these terms together, we can write the interaction Hamiltonian between the nanospin $\mathbf{S}$ and the nuclear spins $\{\mathbf{I}_k\}$ in the form $\mathcal{H}_{NS} = \mathcal{H}_o(\hat{\tau}) + V(\hat{\tau}, \mathbf{I}_k)$, where

$$V = \hat{\tau}_z \sum_k \omega_k^\parallel \hat{l}_k \cdot \hat{\mathbf{I}}_k + \sum_k \omega_k^\perp \hat{m}_k \cdot \hat{\mathbf{I}}_k \quad (3)$$

This form is particularly useful for quantifying the decoherence from the nuclear spins. When we come to particular examples we will specify the couplings in (3).

The magnetoacoustic interaction between the qubit coordinate $\hat{\tau}$ and the phonon coordinate x_q is dominated in nanomagnets [9, 10] by a non-diagonal term $\hat{\tau}_x \sum_q c_q^\perp x_q$. This term has strength

$$c_q^\perp x_q \sim S \Omega_o (\omega_q / \theta_D)^{1/2}, \quad (4)$$

where θ_D is the Debye energy, $\omega_q = qc_s$ and c_s is the sound velocity.

Our basic idea is as follows. The allowed nuclear spin bath states, when the qubit is in some given state, have a density of states which typically has Gaussian lineshape [11], with a halfwidth E_o ; in terms of the $\{\omega_k^\parallel\}$ defined above, E_o is given trivially by

$$E_o^2 = \sum_k \frac{I_k + 1}{3I_k} (\omega_k^\parallel I_k)^2 \quad (5)$$

On the other hand the acoustic phonon energy scale is the Debye energy θ_D . Now in a nanomagnetic system E_o/θ_D can be $\lesssim 10^{-4}$, suggesting the following tactic for suppressing decoherence. If we tune Δ_o so that $\theta_D \gg \Delta_o \gg E_o$, then we will be in a "coherence window", in which decoherence will be at a minimum because the qubit dynamics is too slow to disturb most phonons, but too fast for the nuclear spins to react.

Decoherence Rates: To substantiate this idea, we generalise the low field ($\Delta_o < E_o$) calculations of nanomagnetic dynamics [10], where incoherent tunneling relaxation is found, to the high-field regime $\Delta_o \gg E_o$. Because at high field the couplings $\{\omega_k^\parallel\}$ of the nuclear spins to the qubit are $\ll$ the nuclear Zeeman couplings $\{\omega_k^\perp\}$, and also $\{\omega_k^\parallel\} \ll \Delta_o$, this dynamics can be solved perturbatively [12, 13]. We expand about the bare qubit

Hamiltonian (3) to 2nd order in $\omega_k^\parallel/\Delta$ (assuming $\epsilon_o = 0$ for simplicity) to get

$$\begin{aligned} H_{NS} = & [\Delta_o \hat{\tau}_x + \sum_k \omega_k^\perp \hat{m}_k \cdot \mathbf{I}_k] \\ & + \hat{\tau}_x \sum_{kk'} \frac{\omega_k^\parallel \omega_{k'}^\parallel}{2\Delta_o} (\hat{l}_k \cdot \mathbf{I}_k) (\hat{l}_{k'} \cdot \mathbf{I}_{k'}) \\ & + O((\omega_k^\parallel)^4 / \Delta_o^3) \end{aligned} \quad (6)$$

The decoherence time τ_ϕ is defined as the characteristic time for decay of the off-diagonal density matrix element, starting in state $|\uparrow\rangle$. In the present case we calculate this matrix element as a path integral over pairs of qubit trajectories $\tau_z(t), \tau_z(t')$ (each taking values ± 1 , with occasional flips between these values), weighted by an influence functional $F[\tau_z(t), \tau_z(t')]$ which incorporates the interactions [5]. The contribution from the 2nd term in (6) to this functional is [12, 13]:

$$\ln F = - \sum_k \frac{(\omega_k^\parallel)^2}{8\hbar^2} \left| \int_0^t ds e^{\frac{i}{\hbar} \omega_k^\perp s} [\tau_z(s) - \tau_z'(s)] \right|^2 \quad (7)$$

From this result we can then use standard techniques developed for the spin-boson model [5], to find a contribution γ_ϕ^κ to the dimensionless decoherence rate $\gamma_\phi = 1/\tau_\phi \Delta_o$ (the commonly used 'decoherence quality factor' [3] is just $Q_\phi = \pi/\gamma_\phi$). We find

$$\begin{aligned} \gamma_\phi^\kappa &= \sum_{kk'} \sqrt{\frac{(I_k + 1)(I_{k'} + 1)}{9I_k I_{k'}}} \frac{\omega_k^\parallel \omega_{k'}^\parallel I_k I_{k'}}{2\Delta_o^2} \\ &= \frac{1}{2} \left(\frac{E_o}{\Delta_o} \right)^2 \end{aligned} \quad (8)$$

which decreases rapidly with increasing qubit operating frequency Δ_o .

There are 2 other contributions to γ_ϕ coming from the nuclear spins [10, 13]. First, in writing (3) we omitted a renormalisation of the tunneling matrix element caused by the coupling to the nuclear spins [14], which in fact describes the nuclear spin transitions induced directly by electronic spin flips. This adds a contribution γ_ϕ^λ to γ_ϕ , given by $\gamma_\phi^\lambda = \frac{1}{2} \sum_k |\vec{\alpha}_k|^2$, where $|\vec{\alpha}_k| = \pi |\omega_k^\parallel| / 2\Omega_o$. However when $\Delta_o \gg E_o$, the ratio $\gamma_\phi^\lambda / \gamma_\phi^\kappa \sim O(\Delta_o^2 / \Omega_o^2) \ll 1$ (the usual WKB reduction of the tunneling amplitude), ie., this term can always be neglected to first approximation. Second, we have neglected the intrinsic nuclear spin diffusion dynamics, caused by internuclear interactions. In low fields, when the tunneling is slow, and $\Delta_o \ll E_o$, this intrinsic nuclear dynamics renders the tunneling dynamics incoherent [10, 15, 19, 21]. However when $\Delta_o \gg E_o$, the nuclear fluctuations are very slow compared to the qubit dynamics (of frequency Δ_o); they then add a 'noise' contribution $\gamma_\phi^N \sim N/\pi \Delta_o T_2$ to γ_ϕ , where N is the number of nuclear spins in each molecule

[13]. Typically $T_2^{-1} \sim 10 - 100 \text{ Hz}$ at low T in magnetic molecules [17]), whereas we are interested in $\Delta_o \sim \text{GHz}$ (see below); thus γ_ϕ^N will be very small.

Finally we include the phonon contribution to γ_ϕ . The solution to the spin-boson problem for non-diagonal coupling to phonons [5] gives a contribution γ_ϕ^{ph} of form [10]:

$$\gamma_\phi^{ph} = [(S\Omega_o\Delta_o)^2/\theta_D^4] \coth(\Delta_o/k_B T) \quad (9)$$

which increases rapidly with Δ_o .

The phonon and nuclear spin decoherence mechanisms act independently- thus we can get a simple estimate for the optimal decoherence rate γ_ϕ^{min} by summing the two dominant contributions (8) and (9), and minimizing their sum $\gamma_\phi^N + \gamma_\phi^{ph}$ with respect to Δ_o , assuming $k_B T < \Delta_o$. This gives

$$\gamma_\phi^{min} \approx \sqrt{2} S \Omega_o E_o / \theta_D^2 \quad (10)$$

at an optimal tunneling splitting Δ_o^{opt} :

$$\Delta_o^{(opt)} \approx \theta_D (E_o / \sqrt{2} S \Omega_o)^{1/2}. \quad (11)$$

We see that decoherence is minimized for a given S by making E_o and Ω_o small, and θ_D large, within the constraint that $\Omega_o \gg \Delta_o > k_B T$. If $k_B T > \Delta_o$ we get a different (less favorable) answer.

These simple results actually give reasonably accurate results when compared with numerical calculations on real systems, as we now see.

2. Three Examples: We present quantitative results for the decoherence rates in 3 different materials. We give most details for the *Fe-8* example, to illustrate our method.

(i) The *Fe-8* molecule: This well-characterized molecule [6] behaves below $\sim 10 \text{ K}$ as an electronic spin-10 system, with biaxial effective Hamiltonian [6, 7] $\mathcal{H}_o(\mathbf{S}) \sim -D\hat{S}_z^2 + E\hat{S}_x^2 + K_4^\perp(\hat{S}_+^4 + \hat{S}_-^4) - g\mu_B \mathbf{H}_\perp \cdot \mathbf{S}$, with $D/k_B = 0.23 \text{ K}$, $E/k_B = 0.094 \text{ K}$, and $K_4/k_B = -3.28 \times 10^{-5} \text{ K}$. The small oscillation frequency $\Omega_o = 2SC_4\sqrt{DE} \sim 4.6 \text{ K}$, where $C_4 = 1.56$ includes the effects of the K_4 term; T -independent tunneling dynamics appears below $\sim 0.4 \text{ K}$. The tunneling amplitude $\Delta_o(\mathbf{H}_\perp)$ is trivially determined by diagonalisation of $\mathcal{H}_o(\mathbf{S})$ (Fig. 1), as are the spin orientations $\mathbf{n}^\uparrow, \mathbf{n}^\downarrow$ defined previously. At a critical transverse field H_c the barrier is destroyed and $\mathbf{n}^\uparrow, \mathbf{n}^\downarrow$ merge. When $\mathbf{H}_\perp^\perp$ is along the hard $\hat{x}$ -axis (so the azimuthal angle $\phi = 0$ or π), one has $g\mu_B H_c = 2S(D + E)$ for this Hamiltonian, giving $H_c \sim 4.8 \text{ T}$. We find by comparing exact diagonalisation with semiclassical calculations, that the latter are accurate up to $\mathbf{H}_\perp^\perp \sim 3.3 - 4.3 \text{ T}$ (for $\phi = 90^\circ, 0^\circ$ respectively).

The hyperfine interactions between the 8 Fe^{+3} (spin 5/2) ions and the 205 nuclear spins in the molecule (213 if ^{57}Fe isotopes are substituted for ^{56}Fe nuclei) are of

2 kinds. The *Fe* electronic spins interact with any ^{57}Fe ions via contact hyperfine interactions, which we assume to be the same as for Fe^{+3} ions in similar materials [24]. On the other hand the hyperfine couplings $A_{\alpha\beta}^{jk} s_j^\alpha I_k^\beta$ to all the other nuclear spins are thought to be dominated by purely dipolar terms [15].




FIG. 1: The tunneling splitting $\Delta_o(\mathbf{H}_\perp)$ for the *Fe-8* molecule, for transverse field $\mathbf{H}_\perp$ in the $\hat{x}\hat{y}$ plane, at azimuthal angle ϕ from the in-plane hard axis. We use parameters given in the text [6, 7] for the molecular spin Hamiltonian $\mathcal{H}_o(\mathbf{S})$.

Using the known nuclear positions and moments, the hyperfine interactions and the nuclear Zeeman couplings are then quantified numerically, to find the $\{\omega_k^\parallel\}$ and hence E_o (see Fig. 2), and also the $\{\omega_k^\perp\}$. In spite of the large number of protons, E_o is quite small (particularly when we substitute 2H nuclei for 1H), making *Fe-8* a reasonable candidate for coherent dynamics in high fields. One may also calculate the nuclear dynamics [16], but here we simply note that NMR experiments [17] indicate that at low T , $T_2 \sim 10 - 30 \text{ msec}$ for 1H nuclei in magnetic molecules. We then calculate numerically the different nuclear spin contributions to γ_ϕ (ie., the dominant contribution (8), plus the smaller contributions γ_ϕ^A and γ_ϕ^N), and also the phonon contribution γ_ϕ^{ph} , as a function of $\mathbf{H}_\perp^\perp$.

The results are shown for high fields in Fig. 3. Actually almost all experiments on the quantum dynamics of *Fe-8* have been done in the regime $\Delta_o < E_o$, ie., where we expect nuclear spins to cause incoherent tunneling [10]- which is what is found experimentally [15, 17, 18, 19]. However once Δ_o exceeds E_o , all nuclear spin decoherence should fall off very fast. The nuclear noise contribution $\gamma_\phi^N < 10^{-7}$ once $|\mathbf{H}_\perp^\perp| > 3.2 \text{ T}$ (for $\phi = 0^\circ$) or $> 2 \text{ T}$ (for $\phi > 90^\circ$), so we can safely ignore it. The estimate (10) then gives $\gamma_\phi^{min} \approx 5.8 \times 10^{-5}$ at a $\Delta_o^{opt} \approx 0.14 \text{ K}$, when $\phi = 0$ and $H_o^\perp = 3.45 \text{ T}$ (assuming the optimal set of nuclear isotopes, with 2H instead of 1H , no ^{57}Fe , etc). In Fig. 3 we calculate γ_ϕ numerically, adding all nuclear spin and phonon contributions. For $\phi = 0$ we get a nu-

merical value $\gamma_\phi^{min} = 6 \times 10^{-5}$, at a $\Delta_o^{opt} = 0.135 K$ when $H_o^\perp = 3.45 T$; thus the estimate works well for $\phi = 0$. The further reduction of γ_ϕ^{min} to $\sim 2.4 \times 10^{-6}$, when $\phi \rightarrow 90^\circ$ ($H_o^\perp = 2.93 T$), comes from decreases in both Ω_o and the effective S (since both the tunneling barrier and the change $|\mathbf{S}^\uparrow - \mathbf{S}^\downarrow|$ decrease). Fig. 3 clearly illustrates the window for coherent dynamics which opens up at high transverse fields ($H_o^\perp \sim 2.9 - 3.4 T$, depending on ϕ) in *Fe-8*.




FIG. 2: A histogram of the calculated couplings $\{\omega_k^\parallel\}$ between the *Fe-8* spin-10 and both 1H nuclei and ^{57}Fe nuclei, binned in $0.1 MHz$ intervals (the couplings to the other nuclear species are not displayed). Apart from the core polarisation coupling to ^{57}Fe nuclei, all hyperfine couplings are assumed dipolar, and calculated using the known positions of each nucleus [23]. We assumed Hartree-Fock wave-functions for each Fe^{+3} ion [24] (correcting the results of ref. [25], which used an incorrect coordinate system for the molecule). The insert shows the variation with $H_o^\perp$ of the nuclear multiplet linewidth parameter E_o (see text). Curve (2) has naturally occurring isotopic concentrations. Curve (1) substitutes ^{57}Fe for ^{56}Fe , and curve (3) substitutes 2H for 1H . Previous measurements of the "hole-width" parameter ξ_o , which has E_o as an upper bound (taken from ref. [15]) are also shown for 2 of these cases.

(ii) *Ni*-based particles: Consider now a pure *Ni* particle at low T , with $\Omega_o = 1 K$ and spin S , coupled to a substrate with $\theta_D = 300 K$. The concentration of ^{59}Ni nuclei (spin-1/2) is $x_{59} \sim 0.01$ in natural *Ni*, and the hyperfine coupling $\omega_k^\parallel \rightarrow \omega_o \sim 1.4 mK$. From (10) we have $\gamma_\phi^{min} \sim SE_o/10^5 \sim O(S^{3/2}\omega_o x_{59}^{1/2}/10^5)$, since $E_o \sim \omega_o N^{1/2}$, where $N \sim S$ is the number of nuclear spins. Then in natural *Ni*, γ_ϕ^{min} reaches unity once $S \sim 2.6 \times 10^4$, for a $\Delta_o^{(opt)} \sim 0.2 K$. Isotopic purification by a factor 10^2 (a major undertaking!) would reduce γ_ϕ^{min} by only a factor of 10. Note that *Ni* has an unusually low concentration of nuclear spins, with rather weak hyperfine couplings. Thus this example teaches us that to see any macroscopic coherence effects in tunneling magnets for $S > 10^5$ will require almost complete isotopic

purification (there are no known magnetic species not having at least one natural isotope with non-zero nuclear spin). Note further that we only consider here intrinsic decoherence from phonons and nuclear spins inside the particle- we have ignored electronic decoherence, which certainly exists in *Ni*.




FIG. 3: Calculated behaviour of $\gamma_\phi(H_\perp)$ for an *Fe-8* molecule, using the results for $\Delta_o(H_o^\perp)$, the $\{\omega_k^\parallel(H_\perp)\}$, and E_o (Fig. 1), and also evaluating $\Omega_o(H_\perp)$ as a function of $H_\perp$. We show the individual contributions from γ_ϕ^k for different field orientations in large transverse fields, for γ_ϕ^k (shown for $\phi = 0^\circ$), and for the phonon contribution γ_ϕ^{ph} , assuming a Debye energy $\theta_D = 33 K$ (the small contribution γ_ϕ^N is not shown). Results are shown for the *optimal* distribution of nuclear isotopes, i.e., with 2H substituted for 1H , and only ^{56}Fe , ^{79}Br , ^{14}N and ^{16}O species in the molecule.

(iii) *Ho* ions: Not all systems will have an optimal intrinsic decoherence described by (10). Consider the $LiHo_xY_{1-x}F_4$ system [20], in which sharp absorption lines are seen [21, 22] at low x . The Ho^{+3} ions (with spin = 8) have a lowest doublet state, with splitting $\Delta_o \propto |H_o^\perp|^2$ in a transverse field- only one other state, at an energy $\Omega_o \sim 10.6 K$, is important for the low-energy physics (all other electronic spins levels are at energies $\gtrsim 100 K$). The new feature here, which renders (10) inapplicable, is a very strong hyperfine coupling $\omega_{Ho}^\parallel = 0.039 K$ to the $I = 7/2$ *Ho* nuclear spin- whereas the couplings to the "satellite" *Li*, *Y*, and *F* nuclear spins are very weak. Thus instead of having a Gaussian lineshape, the hyperfine multiplet has a "toothcomb" structure with 15 *Ho* lines spaced in intervals of $0.039 K$, each weakly broadened (by less than $1 mK$) by the other nuclei. The quantity E_o is then not well-defined [11]. However one may instead just calculate the coupled *Ho*-nuclear spin dynamics in 2nd-order perturbation theory, since $\Omega_o \gg$ all hyperfine couplings, and all *Ho* transitions go via the single intermediate level. We then find the optimal strategy is to (a) freeze the *Ho* nuclei by cool-

ing to $k_B T \ll 0.039 K$, and (b) make $\mathbf{H}_o^\perp$ large enough so that precessional decoherence from the satellite nuclei is eliminated, but small enough so that Ho nuclei are weakly excited. We find that at $T = 3 mK$, tuning of Δ_o to $30 mK$ (using $\mathbf{H}_o^\perp \sim 0.3 T$) gives a contribution $\gamma_\phi^{min} \sim 1.8 \times 10^{-5}$ from the Ho nuclei (phonons giving a contribution $< 10^{-9}$ here). Some residual decoherence also comes from the 'satellite' nuclear spins- in this context it is interesting that Ho^{+3} ions can be prepared in hosts with almost no other nuclear spins (eg., $CaWO_4$, with isotopically purified W ; see [21]). Thus we can expect a reduction of γ_ϕ^{min} to very low levels, limited only by a weak phonon effect, external noise, and any spin impurities.

3. Discussion: In insulating systems where nuclear spin decoherence is suppressed by a transverse field, decoherence optimisation is well described by (10). This means having a small S , small E_o , and a "stiff" system (high θ_D). Surprisingly it also means low Ω_o , ie., weak magnetic anisotropy. By taking all these measures, very low values of γ_ϕ can be attained.

Our results are thus good news for coherence in small nanomagnets, and magnetic qubits. In most materials a correct choice of parameters requires strong transverse fields, but in systems like $LiHo_xY_{1-x}F_4$ with one very strong hyperfine coupling $\omega_o^\parallel$, and otherwise weak or non-existent ones, it pays to keep Δ_o low (ie., not too strong fields), and to have $kT \ll \omega_o^\parallel$ (to suppress thermal nuclear spin noise).

For genuinely macroscopic superpositions of magnetic states, the result (10) is not such good news. Although one may stave off decoherence for large S by isotopic purification of nuclear spins, our Ni example shows this tactic reaches its limit once $S \sim 10^5 - 10^6$.

So far experiments on nanomagnets have concentrated on field ranges where $\Delta_o < E_o$, and so incoherent tunneling is observed- any experiments on, eg., $Fe-8$ in the range $|\mathbf{H}_o^\perp| \sim 3 - 4 T$ would be of great interest. In almost all experiments so far, on molecules or rare earth ions, collective tunneling caused by inter-spin dipolar interactions complicate the interpretation [20, 21, 22]. A clean observation of coherence, with a measurement of γ_ϕ , will thus involve manipulation at microwave frequencies, on a properly isolated single system.

We thank G.A. Sawatzky for useful discussions, and NSERC, the CIAR, and grant number NS-1767.2003.2 in Russia, for support.

- Lett. **78**, 3366 (1997); I.L. Aleiner, B.L. Altshuler, M.E. Gershenson, *Waves in Random Media* **9**, 201 (1999).
- [3] C.H. van der Wal, et al., *Science* **290**, 773 (2000); Y. Nakamura, Yu. A. Pashkin, T. Yamamoto, J.S. Tsai, *Phys. Rev. Lett.* **88**, 047901 (2002); D. Vion et al., *Science* **296**, 886 (2002).
- [4] A.J. Leggett et al. *Rev. Mod. Phys.* **59**, 1 (1987)
- [5] U. Weiss, "*Dissipative Quantum Systems*" (World Scientific, 1999)
- [6] W. Wernsdorfer, *Adv. Chem. Phys.* **118**, 99 (2001)
- [7] I.S. Tupitsyn, B. Barbara, pp. 109-168 in "*Magnetoscience - from Molecules to Materials, vol. 3*", ed. Miller & Drillon (Wiley, 2001).
- [8] A. Auerbach, "*Interacting Electrons and Quantum Magnetism*" (Springer-Verlag, 1994)
- [9] P. Politi, A. Rettori, F. Hartmann-Boutron, J. Villain, *Phys. Rev. Lett.* **75**, 537 (1995).
- [10] N.V. Prokof'ev, P.C.E. Stamp, *J. Low Temp. Phys.* **104**, 143 (1996)
- [11] The Gaussian lineshape follows directly from the central limit theorem if the number N of nuclear spins is large, *unless* all the $\omega_k^\parallel$ have very similar values, and/or one species dominates all the others. In this case one expects a 'toothcomb' pattern [10] in the density of states. This is precisely what happens in the case of $LiHo_xY_{1-x}F_4$ (see ref. [21]).
- [12] A.O. Caldeira, A.H. Castro-Neto, T.O. deCarvalho, *Phys. Rev. B* **48**, 13974 (1993)
- [13] N.V. Prokof'ev, P.C.E. Stamp, *Rep. Prog. Phys.* **63**, 669 (2000)
- [14] A systematic truncation of the microscopic hyperfine interaction between nuclear spins and qubit gives the renormalisation $\Delta_o \hat{\tau}_x \rightarrow \frac{1}{2} [\Delta \exp^i \sum_k \vec{\alpha}_k \cdot \mathbf{I}_k + H.c.]$, where $\vec{\alpha}_k$ can be calculated from the microscopic Hamiltonian (see I. Tupitsyn et al., *Int. J. Mod. Phys B* **11**, 2901 (1997)). However this can usually be neglected- see text.
- [15] W. Wernsdorfer, A. Caneschi, R. Sessoli, D. Gatteschi, A. Cornia, V. Villar, C. Paulsen, *Phys. Rev. Lett.* **84**, 2965 (2000)
- [16] B. Fine (unpublished).
- [17] Y. Furukawa et al., *Phys. Rev. B* **64**, 094439 (2001); Y. Furukawa et al., *Phys. Rev. B* **67**, 064426 (2003); A. Morello et al., *Polyhedron* **22**, 1745 (2003); and to be published
- [18] C. Sangregorio, T. Ohm, C. Paulsen, R. Sessoli, D. Gatteschi, *Phys. Rev. Lett.* **78**, 4645 (1997)
- [19] T. Ohm et al., *Europhys. J. B* **6**, 595 (1998); L. Thomas et al., *Phys. Rev. Lett.* **83**, 2398 (1999), W. Wernsdorfer et al., *Phys. Rev. Lett.* **82**, 3903 (1999); and refs. therein.
- [20] J. Brooke, T.F. Rosenbaum, G. Aeppli, *Nature* **413**, 610 (2001)
- [21] R. Giraud, W. Wernsdorfer, A.M. Tkachuk, D. Mailly, B. Barbara, *Phys. Rev. Lett.* **87**, 057203 (2001)
- [22] S. Ghosh, R. Parthasarathy, T. F. Rosenbaum, G. Aeppli, *Science* **296**, 2195 (2002)
- [23] Cambridge Data base: www.ccdc.cam.ac.uk.
- [24] A.J. Freeman, A.J. Watson, pp. 291 in "*Magnetism II*", ed. G. Rado, H. Suhl (Academic, 1963)
- [25] G. Rose, Ph.D. thesis (University of British Columbia, 2000)

[1] See, eg., J. Preskill, *Proc. Roy. Soc A* **454**, 385 (1998).

[2] P. Mohanty, E.M.Q. Jariwala, R.A. Webb, *Phys. Rev.*